

Chemical Resistance



For further details regarding any of the testing by Urban Hygiene Ltd, please contact:

Email: enquiries@urbanhygiene.com

Telephone: **+44 (0) 1302 623193**

Or visit: www.urbanhygiene.com

CHEMICAL RESISTANCE

The following chemicals were tested for a 24 hour exposure period and scores given based on 10 being the maximum achievable and 1 being the lowest.

Sodium Hydroxide 50%	10
Hydrochloric Acid Conc	10
Sulphuric Acid 93%	6
Phenol	8
Phosphoric Acid	10
Acetone	10
Ammonium Hydroxide Conc	10
Ethyl Alcohol	10